

Stucco Originale – interior

High-quality, decorative, matt plaster based on synthetic resin dispersion, with a beautiful and authentic stucco appearance. For interior use.

Properties: Ready-to-use, very easy to process, available in various colours from the Stucco d'Or colour collection, various structural effects possible, odourless and solvent free.

Application: Stucco d'Or Stucco Originale is only used indoors as a decorative finishing layer on all load-bearing, flat-set, clean and dry surfaces such as cement and plaster, concrete, brick, plasterboard and existing paint layers. For optimal protection, finish with Stucco d'Or Protecto 1K Mat after drying. In case of application in the kitchen, bathroom or toilet, always finish with Stucco d'Or Protecto 2K Mat. When using in a kitchen, place protection (stainless steel or glass plate) directly behind the hob. In case of application to special areas, we advise you to consult our technical advisor.

PROCESSING	APPLICATION
Application	Mix Stucco d'Or Stucco Originale well before use. Apply in two layers. Apply a first layer of opaque using a stainless steel Stucco trowel. After drying, apply a second layer with stainless steel Stucco trowel to create the desired concrete effect.
Dilution	Ready to use. Dilution is not necessary.
Consumption	0.1 mm grain 0.4 - 0.6 kg/m ² in two layers. 0.3 mm grain 1.3 - 1.6 kg/m ² in two layers. 0.5 mm grain 1.6 - 1.9 kg/m ² in two layers. The stated yield is theoretical. The actual consumption depends on the nature and structure of the surface and the application method.
Drying time (at 20 °C, 65% relative air humidity)	Dust dry after ± 2 hours. The second layer can be applied after ± 6 hours, cured after a few days. Longer drying times are naturally required at a lower temperature and higher humidity.
Processing temperature/Relative humidity	Do not process if the surface and ambient temperature is below 8 °C and relative humidity greater than 80%.
Cleaning tools	Thoroughly clean tools immediately after use using warm water.

SURFACE	PRE-TREATMENT
General	The surface must be flat, load-bearing, dry, clean, and free of grease, wax, silicone and dust. Any cracks, gaps, and unstable surfaces must be repaired. Always pre-treat the surface in the same colour of the final finish.
Untreated surfaces such as plaster, concrete, plasterboard	Ensure the surface is dust-free. Afterwards: <ul style="list-style-type: none"> - When finishing with Stucco Originale 0.1 mm, pre-treat the surface with Stucco d'or Primo. Drying time 6 hours minimum. - When finishing with Stucco Originale 0.3 mm or 0.5 mm, pre-treat the surface with a plaster primer with fine quartz grains (PRINSSSEN Ruwer). Drying time 18 hours minimum.
Non load-bearing (powdery) surfaces	Clean the surface and then pre-treat with a fixation primer (PRINSSSEN Diepgrond). Afterwards: <ul style="list-style-type: none"> - When finishing with Stucco Originale 0.1 mm, pre-treat the surface with Stucco d'or Primo. Drying time 6 hours minimum. - When finishing with Stucco Originale 0.3 mm or 0.5 mm, pre-treat the surface with a plaster primer with fine quartz grains (PRINSSSEN Ruwer). Drying time 18 hours minimum.
Load-bearing, slightly contaminated surfaces	Clean/remove contamination with a cleaning agent. Afterwards: <ul style="list-style-type: none"> - When finishing with Stucco Originale 0.1 mm, pre-treat the surface with a stain insulating wallpaint (PRINSSSEN Isomat). Drying time 24 hours minimum. - When finishing with Stucco Originale 0.3 mm or 0.5 mm, pre-treat the surface with a stain insulating plaster primer with fine quartz grains (PRINSSSEN ISO Ruwer). Drying time 24 hours minimum.
Load-bearing, heavily contaminated surfaces	Isolate local contaminants with a stain insulating primer (PRINSSSEN Isoleerspray). Treat large surfaces with a stain insulating primer (PRINSSSEN Isoleergrond). Afterwards: <ul style="list-style-type: none"> - When finishing with Stucco Originale 0.1 mm, pre-treat the surface with a stain insulating wallpaint (PRINSSSEN Isomat). Drying time 24 hours minimum. - When finishing with Stucco Originale 0.3 mm or 0.5 mm, pre-treat the surface with a stain insulating plaster primer with fine quartz grains (PRINSSSEN ISO Ruwer). Drying time 24 hours minimum.
Smooth surfaces (such as lacquer paint layers)	Clean and degrease the surface. After drying, lightly roughen, carefully remove dust and then: <ul style="list-style-type: none"> - When finishing with Stucco Originale 0.1 mm, pre-treat the surface with Stucco d'or Primo. Drying time 6 hours minimum. - When finishing with Stucco Originale 0.3 mm or 0.5 mm, pre-treat the surface with a plaster primer with fine quartz grains (PRINSSSEN Ruwer). Drying time 18 hours minimum.
Surfaces with non-waterproof coatings (such as smudge-proof)	Clean the surface thoroughly with clean water until it no longer expels water. After drying, pre-treat with a fixation primer (PRINSSSEN Diepgrond). Then: <ul style="list-style-type: none"> - When finishing with Stucco Originale 0.1 mm, pre-treat the surface with Stucco d'or Primo. Drying time 6 hours minimum. - When finishing with Stucco Originale 0.3 mm or 0.5 mm, pre-treat the surface with a plaster primer with fine quartz grains (PRINSSSEN Ruwer). Drying time 18 hours minimum.
Surface with wall paint	Clean the surface thoroughly. After allowing to dry: <ul style="list-style-type: none"> - When finishing with Stucco Originale 0.1 mm, pre-treat the surface with Stucco d'or Primo. Drying time 6 hours minimum. - When finishing with Stucco Originale 0.3 mm or 0.5 mm, pre-treat the surface with a plaster primer with fine quartz grains (PRINSSSEN Ruwer). Drying time 18 hours minimum.

Stucco d'Or

PRINSSSEN

Surfaces with ornamental plaster	Clean the surface thoroughly. After drying, level with gypsum plaster. After complete drying: <ul style="list-style-type: none">- When finishing with Stucco Originale 0.1 mm, pre-treat the surface with Stucco d'or Primo. Drying time 6 hours minimum.- When finishing with Stucco Originale 0.3 mm or 0.5 mm, pre-treat the surface with a plaster primer with fine quartz grains (PRINSSSEN Ruwer or PRINSSSEN ISO Ruwer). Drying time 24 hours minimum.
Applicable for all surfaces	Important: Allow sufficient drying time between various pre-treatments.

TECHNICAL DATA	VALUE
Density	Approx. 1,55 kg/L
Binding agent	Synthetic resin dispersion
Solid components	Approx. 50% v/v
Colours	Standard white. Available in various colours from the Stucco d'Or colour collection using the PRINSSSEN colour mixing system.
Degree of gloss	Matt
Storage	Protect from frost during transportation and storage. Keep container tightly closed. Can be stored for at least 12 months.
Hazards	See applicable Safety Data Sheet.

General comment:

If the surface and ambient temperature is too low, or the relative humidity too high and/or the moisture content of the surface is too high, these parameters must be reduced to the prescribed requirements. This can be achieved using heating, moisture extractors, ventilation, etc. It is necessary to continue using these measures during the application and the entire curing process.

The information published here is based on our current level of knowledge and experience. Due to the large number of possible factors that influence the application and use of our products, this information in no way releases the party using the product from its responsibility to carry out its own checks and tests. The information we have provided in no way guarantees specific properties or the suitability of the product for a specific application. All of the descriptions, drawings, photos, data, ratios, weights, etc. referred to here are purely of a general nature; they may change without prior notice and do not reflect the contractually agreed quality of the products (product specification). Possible property rights and existing laws and regulations must be taken into account by the recipient of our products to take personal responsibility into account. All previous Technical Datasheets are invalid upon publication of this document.

Version 19-11-2018